



US007001482B2

(12) **United States Patent**
Landis et al.

(10) **Patent No.:** **US 7,001,482 B2**

(45) **Date of Patent:** **Feb. 21, 2006**

(54) **METHOD AND APPARATUS FOR IMPROVED FOCUS RING**

- (75) Inventors: **Michael Landis**, Gilbert, AZ (US);
Steven T Fink, Mesa, AZ (US)
- (73) Assignee: **Tokyo Electron Limited**, Tokyo (JP)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/705,221**
(22) Filed: **Nov. 12, 2003**

(65) **Prior Publication Data**
US 2005/0099135 A1 May 12, 2005

- (51) **Int. Cl.**
C23F 1/02 (2006.01)
C25D 3/38 (2006.01)
C23C 16/00 (2006.01)
- (52) **U.S. Cl.** **156/345.55**; 156/345.51;
156/345.54; 204/298.28; 204/298.23; 118/730;
118/728
- (58) **Field of Classification Search** 156/345,
156/345.55, 345.54, 345.51; 204/298, 298.28,
204/298.23; 118/715, 723, 730, 729, 728;
315/111.71, 111

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,556,500 A	9/1996	Hasegawa et al.	
6,815,352 B1 *	11/2004	Tamura et al.	438/691
6,837,966 B1 *	1/2005	Nishimoto et al.	156/345.29
2001/0015262 A1	8/2001	Denpoh	
2002/0072240 A1	6/2002	Koike	
2004/0125360 A1 *	7/2004	Ludviksson et al.	356/72


* cited by examiner

Primary Examiner—Tuyet Thi Vo
(74) *Attorney, Agent, or Firm*—Pillsbury Winthrop Shaw Pittman LLP

(57) **ABSTRACT**

A focus ring assembly, configured to be coupled to a substrate holder in a plasma processing system, comprises a focus ring having one or more wear indicators for determining the lifetime of the focus ring, wherein the coupling of the focus ring to the substrate holder facilitates auto-centering of the focus ring in the plasma processing system. For example, a centering ring mounted on the substrate holder can comprise a centering feature configured to couple with a mating feature on the focus ring.

16 Claims, 9 Drawing Sheets






FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 6




FIG. 7




FIG. 8




FIG. 9

METHOD AND APPARATUS FOR IMPROVED FOCUS RING

FIELD OF THE INVENTION

The present invention relates to a method and apparatus for utilizing a focus ring in a plasma processing system and, more particularly, to a focus ring assembly that facilitates improved maintenance of the plasma processing system.

BACKGROUND OF THE INVENTION

The fabrication of integrated circuits (IC) in the semiconductor industry typically employs plasma to create and assist surface chemistry within a vacuum processing system necessary to remove material from and deposit material to a substrate. In general, plasma is formed within the processing system under vacuum conditions by heating electrons to energies sufficient to sustain ionizing collisions with a supplied process gas. Moreover, the heated electrons can have energy sufficient to sustain dissociative collisions and, therefore, a specific set of gases under predetermined conditions (e.g., chamber pressure, gas flow rate, etc.) are chosen to produce a population of charged species and chemically reactive species suitable to the particular process being performed within the system (e.g., etching processes where materials are removed from the substrate or deposition processes where materials are added to the substrate).

Although the formation of a population of charged species (ions, etc.) and chemically reactive species is necessary for performing the function of the plasma processing system (i.e. material etch, material deposition, etc.) at the substrate surface, other component surfaces on the interior of the processing chamber are exposed to the physically and chemically active plasma and, in time, can erode. The erosion of exposed components in the processing system can lead to a gradual degradation of the plasma processing performance and ultimately to complete failure of the system.

Therefore, in order to minimize the damage sustained by exposure to the processing plasma, a consumable or replaceable component, such as one fabricated from silicon, quartz, alumina, carbon, or silicon carbide, can be inserted within the processing chamber to protect the surfaces of more valuable components that would impose greater costs during frequent replacement and/or to affect changes in the process. Furthermore, it is desirable to select surface materials that minimize the introduction of unwanted contaminants, impurities, etc. to the processing plasma and possibly to the devices formed on the substrate. Often times, these consumables or replaceable components are considered part of the process kit, which is frequently maintained during system cleaning.

SUMMARY OF THE INVENTION

A method and apparatus for utilizing a focus ring in a plasma processing system is described.

According to one aspect, a focus ring assembly for surrounding a substrate on a substrate holder in a plasma processing system comprises a centering ring configured to be coupled to the substrate holder and a focus ring comprising an upper surface, a lower surface, and one or more wear indicators coupled to at least one of the upper surface and the lower surface, wherein the focus ring is configured to be centered about the substrate by coupling the focus ring to the centering ring.

According to another aspect, a disposable focus ring for surrounding a substrate on a substrate holder in a plasma processing system comprises a ring configured to be coupled to the substrate holder comprising an upper surface, a lower surface, and one or more wear indicators coupled to at least one of the upper surface and the lower surface, wherein the ring is configured to be centered about the substrate by coupling the ring to the substrate holder.

Additionally, a method of replacing a focus ring surrounding a substrate on a substrate holder in a plasma processing system comprises removing a first focus ring from the plasma processing system and installing a second focus ring in the plasma processing system by coupling the second focus ring to the substrate holder. The coupling facilitates auto-centering of the second focus ring in the plasma processing system, wherein the first focus ring and the second focus ring each comprise an upper surface, a lower surface, and one or more wear indicators coupled to at least one of the upper surface and the lower surface.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

FIG. 1 illustrates a schematic block diagram of a plasma processing system according to an embodiment of the present invention;

FIG. 2 presents a plan view of a focus ring according to an embodiment of the present invention;

FIG. 3 presents cross-sectional view of the focus ring depicted in FIG. 2;

FIG. 4A presents an expanded cross-sectional view of the focus ring depicted in FIG. 2;

FIG. 4B presents another expanded cross-sectional view of a focus ring like the one depicted in FIG. 2;

FIG. 5A illustrates the evolution of a wear indicator during processing according to one embodiment of the present invention;

FIG. 5B illustrates the evolution of a wear indicator during processing according to another embodiment of the present invention;

FIG. 6 presents a plan view of a centering ring according to an embodiment of the present invention;

FIG. 7 presents a cross-sectional view of the centering ring depicted in FIG. 5;

FIG. 8 presents an expanded cross-sectional view of the centering ring depicted in FIG. 7; and

FIG. 9 presents a method of replacing a focus ring surrounding a substrate in a plasma processing system.

DETAILED DESCRIPTION OF SEVERAL EMBODIMENTS

In plasma processing, a focus ring can, for example, be configured to surround a substrate on a substrate holder, and be employed to adjust and/or control the properties of the process chemistry local to the peripheral edge of the substrate. For conventional plasma processing systems, the focus ring comprises a ring of silicon, for instance for oxide etching, that rests atop the substrate holder and surrounds the substrate periphery.

According to an embodiment of the present invention, a plasma processing system 1 is depicted in FIG. 1 comprising a plasma processing chamber 10, an upper assembly 20, an electrode plate assembly 24, a substrate holder 30 for supporting a substrate 35, and a pumping duct 40 coupled to a vacuum pump (not shown) for providing a reduced pressure atmosphere 11 in plasma processing chamber 10.

Plasma processing chamber **10** can facilitate the formation of a processing plasma in process space **12** adjacent substrate **35**. The plasma processing system **1** can be configured to process substrates of any size, such as 200 mm substrates, 300 mm substrates, or larger.

In the illustrated embodiment, electrode plate assembly **24** comprises an electrode plate **26** (FIG. 1) and an electrode **28** (FIG. 1). In an alternate embodiment, upper assembly **20** can comprise at least one of a cover, a gas injection assembly, and an upper electrode impedance match network. The electrode plate assembly **24** can be coupled to an RF source. In another alternate embodiment, the upper assembly **20** comprises a cover coupled to the electrode plate assembly **24**, wherein the electrode plate assembly **24** is maintained at an electrical potential equivalent to that of the plasma processing chamber **10**. For example, the plasma processing chamber **10**, the upper assembly **20**, and the electrode plate assembly **24** can be electrically connected to ground potential.

Plasma processing chamber **10** can further comprise an optical viewport **16** coupled to a deposition shield **14**. Optical viewport **16** can comprise an optical window **17** coupled to the backside of an optical window deposition shield **18**, and an optical window flange **19** can be configured to couple optical window **17** to the optical window deposition shield **18**. Sealing members, such as O-rings, can be provided between the optical window flange **19** and the optical window **17**, between the optical window **17** and the optical window deposition shield **18**, and between the optical window deposition shield **18** and the plasma processing chamber **10**. Optical viewport **16** can permit monitoring of optical emission from the processing plasma in process space **12**.

Substrate holder **30** can further comprise a vertical translational device **50** surrounded by a bellows **52** coupled to the substrate holder **30** and the plasma processing chamber **10**, and configured to seal the vertical translational device **50** from the reduced pressure atmosphere **11** in plasma processing chamber **10**. Additionally, a bellows shield **54** can be coupled to the substrate holder **30** and configured to protect the bellows **52** from the processing plasma. Substrate holder **30** can further be coupled to at least one of a focus ring **60**, and a shield ring **62**. Furthermore, a baffle plate **64** can extend about a periphery of the substrate holder **30**.

Substrate **35** can be transferred into and out of plasma processing chamber **10** through a slot valve (not shown) and chamber feed-through (not shown) via robotic substrate transfer system where it is received by substrate lift pins (not shown) housed within substrate holder **30** and mechanically translated by devices housed therein. Once substrate **35** is received from substrate transfer system, it is lowered to an upper surface of substrate holder **30**.

Substrate **35** can be affixed to the substrate holder **30** via an electrostatic clamping system. Furthermore, substrate holder **30** can further include a cooling system including a re-circulating coolant flow that receives heat from substrate holder **30** and transfers heat to a heat exchanger system (not shown), or when heating, transfers heat from the heat exchanger system. Moreover, gas can be delivered to the back-side of substrate **35** via a backside gas system to improve the gas-gap thermal conductance between substrate **35** and substrate holder **30**. Such a system can be utilized when temperature control of the substrate is required at elevated or reduced temperatures. In other embodiments, heating elements, such as resistive heating elements, or thermo-electric heaters/coolers can be included.

In the illustrated embodiment shown in FIG. 1, substrate holder **30** can comprise an electrode through which RF power is coupled to the processing plasma in process space **12**. For example, substrate holder **30** can be electrically biased at a RF voltage via the transmission of RF power from a RF generator (not shown) through an impedance match network (not shown) to substrate holder **30**. The RF bias can serve to heat electrons to form and maintain plasma. In this configuration, the system can operate as a reactive ion etch (RIE) reactor, wherein the chamber and upper gas injection electrode serve as ground surfaces. A typical frequency for the RF bias can range from about 1 MHz to about 100 MHz, for example, about 13.56 MHz. RF systems for plasma processing are well known to those skilled in the art.

Alternately, the processing plasma in process space **12** can be formed using a parallel-plate, capacitively coupled plasma (CCP) source, an inductively coupled plasma (ICP) source, any combination thereof, and with and without magnet systems. Alternately, the processing plasma in process space **12** can be formed using electron cyclotron resonance (ECR). In yet another embodiment, the processing plasma in process space **12** is formed from the launching of a Helicon wave. In yet another embodiment, the processing plasma in process space **12** is formed from a propagating surface wave.

Referring now to an illustrated embodiment of the present invention depicted in FIG. 2 (top plan view), and FIG. 3 (cross sectional view), focus ring **60** can form a ring comprising an upper surface **82**, a lower surface **84**, an inner radial edge **86**, and an outer radial edge **88**. The focus ring **60** can be formed from at least one of silicon, quartz, silicon carbide, silicon nitride, carbon, alumina, sapphire, Teflon, and polyimide. The focus ring **60** can have a thickness ranging from about 0.5 to about 10 mm. Alternatively, the thickness can range from about 1 to about 5 mm, or the thickness can be approximately 1 mm. The focus ring **60** can, for example, be fabricated using at least one of machining, laser-cutting, grinding, and polishing.

FIG. 4A and FIG. 4B provide an expanded cross-sectional view of the focus ring **60**, wherein the focus ring **60** comprises at least one wear indicator **90** coupled to the lower surface **84** and configured to indicate the extent of consumption of the focus ring during processing. Alternately, the focus ring **60** comprises at least one wear indicator **90** coupled to the upper surface **82** and configured to indicate the extent of consumption of the focus ring during processing. For example, FIG. 4A depicts a wear indicator **90** having a constant length and width. Alternatively, FIG. 4B depicts several wear indicators **90**, **90'**, **90''**, each having a different length, and/or different width.

Referring now to FIG. 5A, when the one or more wear indicators **90** are coupled to lower surface **84** of focus ring **60**, each wear indicator **90** is not exposed to the processing environment until a process time (i.e., $T_1 - T_0$) has elapsed that is sufficiently long for the upper surface **82** (that is exposed to the processing environment) to erode to a depth intersecting with the wear indicator. Once the wear indicator **90** is exposed and is now visible from the upper surface **82** of focus ring **60**, the focus ring **60** can be scheduled for replacement. This observation can be made from run-to-run, while monitoring the focus ring **60** through the optical window **17**. Alternatively, as shown in FIG. 5B, when the one or more wear indicators **90** are coupled to upper surface **82** of focus ring **60**, each wear indicator **90** is exposed to the processing environment and, hence, subject to erosion, wherein both the lateral and longitudinal extent of erosion increases from time t_0 to t_1 , t_2 , t_3 , etc. Once the wear

5

indicator **90** has expanded to a pre-determined size, the focus ring **60** can be scheduled for replacement. This observation can be made from run-to-run, while monitoring the focus ring **60** through the optical window **17**.

Additionally, wear indicators **90** can be placed at different radial locations on the focus ring **60** in order to observe radial variations in the consumption of the focus ring **60**. Alternatively, wear indicators can be placed at different azimuthal locations on the focus ring **60** in order to observe azimuthal variations in the consumption of the focus ring **60**. A wear indicator **90** can have a length ranging from about 1 to about 5 mm. Alternatively, the length can range from about 0.25 to about 1 mm, or the length can be approximately 0.5 mm. Alternately, a wear indicator **90** can be a fraction of the thickness of focus ring **60** within a fractional range from about 10 to about 90%. Alternatively, the fraction of the focus ring thickness can have a fractional range from about 25 to about 75%, or the fraction of the focus ring thickness can be approximately 50%. The one or more wear indicators can, for example, be fabricated using at least one of machining, etching, laser-milling, and sonic-milling.

According to an embodiment of the present invention, focus ring **60** can be automatically centered on a substrate holder by coupling a mating feature on the focus ring with a centering feature on the substrate holder. For example, the mating feature on focus ring **60** comprises a mating surface **87** on the outer radial edge **86** (see FIG. **3**). Additionally, the centering feature on the substrate holder can comprise a centering ring coupled to the substrate holder. FIG. **6** presents a plan view of a centering ring **100**, FIG. **7** presents a cross-sectional view of the centering ring **100**, and FIG. **8** presents an expanded cross-sectional view of the centering ring **100**. The centering ring **100** can comprise a flange region **110**, and a lip region **112**, wherein the lip region **112** further comprises a centering surface **120**. The centering surface **120** can, for example, comprise a radial surface as shown in FIGS. **6**, **7**, and **8**, wherein a radial locational clearance fit is provided between the mating surface **87** and the centering surface **120** upon coupling of the focus ring **60** to the centering ring **100**.

Referring still to FIGS. **6** through **8**, centering ring **100** can further comprise two or more locating features **130**, such as two holes, for coupling the centering ring **100** to the substrate holder. The centering ring **100** can rest atop the substrate holder. Alternately, the centering ring **100** can be mechanically clamped to the substrate holder using at least one of a clamp ring and a fastener. Alternately, the centering ring **100** can be electrically clamped to the substrate holder using an electrostatic clamping (ESC) system.

The centering ring **100** can be made from at least one of aluminum, coated aluminum, silicon, quartz, silicon carbide, silicon nitride, carbon, alumina, sapphire, Teflon, and polyimide. For coated aluminum, the coating can, for instance, facilitate the provision of an erosion resistant surface when the centering ring **100** is exposed to harsh processing environments, such as plasma. During fabrication, one or more surfaces can be anodized, one or more surfaces can have a coating sprayed on, or one or more surfaces can be subjected to plasma electrolytic oxidation. The coating can include at least one of a III-column element and a Lanthanum element, for example. The coating can comprise at least one of Al₂O₃, Yttria (Y₂O₃), Sc₂O₃, Sc₂F₃, YF₃, La₂O₃, CeO₂, Eu₂O₃, and DyO₃. Methods of anodizing aluminum components and applying spray coatings are well known to those skilled in the art of surface material treatment.

Referring now to FIG. **9**, a method for replacing a focus ring surrounding a substrate on a substrate holder in a

6

plasma processing system is described. The method comprises a flow chart **200** beginning in **210** with removing a first focus ring from the plasma processing system, wherein the focus ring comprises an upper surface, a lower surface, and one or more wear indicators coupled to at least one of the upper surface and the lower surface. Removing the first focus ring can, for example, comprise venting the plasma processing system to atmospheric conditions and opening the plasma processing chamber to access the interior, followed by decoupling the focus ring from the substrate holder. Decoupling the focus ring from the substrate holder can, for example, comprise lifting the focus ring away from the substrate holder, or de-clamping the focus ring from the substrate holder and then lifting the focus ring away from the substrate holder.

In **220**, a second focus ring is installed in the plasma processing system by coupling the second focus ring to the substrate holder, wherein the coupling facilitates auto-centering of the second focus ring in the plasma processing system. The second focus ring can comprise the first focus ring following refurbishing, or it can be a newly fabricated focus ring having an upper surface, a lower surface, and one or more wear indicators coupled to at least one of said upper surface and said lower surface. Auto-centering of the second focus ring in the plasma processing system can be achieved, as described above, by providing a mating surface on an outer radial edge of the focus ring, and coupling the mating surface to a centering surface on a lip region of a centering ring mounted on the substrate holder. Alternately, auto-centering of the second focus ring in the plasma processing system can be achieved by providing two or more pins mounted on a contact surface on the focus ring, and coupling the pins on the focus ring to two or more receiving holes on a receiving surface of the centering ring. Alternatively, the two or more pins can be located on the centering ring, and the two or more receiving holes can be located on the focus ring.

Although only certain exemplary embodiments of this invention have been described in detail above, those skilled in the art will readily appreciate that many modifications are possible in the exemplary embodiments without materially departing from the novel teachings and advantages of this invention. Accordingly, all such modifications are intended to be included within the scope of this invention.

What is claimed is:

1. A focus ring assembly for surrounding a substrate on a substrate holder in a plasma processing system comprising:
 - a centering ring configured to be coupled to said substrate holder; and
 - a focus ring comprising an upper surface, a lower surface, and one or more wear indicators coupled to at least one of said upper surface and said lower surface, wherein said focus ring is configured to be centered about said substrate by coupling said focus ring to said centering ring.
2. A disposable focus ring for surrounding a substrate on a substrate holder in a plasma processing system comprising:
 - a ring configured to be coupled to said substrate holder comprising an upper surface, a lower surface, and one or more wear indicators coupled to at least one of said upper surface and said lower surface, wherein said ring is configured to be centered about said substrate by coupling said ring to said substrate holder, and
 - wherein said one or more wear indicators comprise a hole in said upper surface or lower surface and extending to

7

a depth from said upper surface or said lower surface, said depth comprising a fraction of the distance between said upper surface and said lower surface.

3. A method of replacing a focus ring surrounding a substrate on a substrate holder in a plasma processing system comprising:

removing a first focus ring from said plasma processing system; and

installing a second focus ring in said plasma processing system by coupling said second focus ring to said substrate holder, said coupling facilitating auto-centering of said second focus ring in said plasma processing system,

wherein said first focus ring and said second focus ring each comprise an upper surface, a lower surface, and one or more wear indicators coupled to at least one of said upper surface and said lower surface, and

wherein said one or more wear indicators comprise a hole in said upper surface or lower surface and extending to a depth from said upper surface or said lower surface, said depth comprising a fraction of the distance between said upper surface and said lower surface.

4. A focus ring assembly for surrounding a substrate on a substrate holder in a plasma processing system comprising:

a centering ring configured to be coupled to said substrate holder; and

a focus ring comprising an upper surface, a lower surface, and one or more wear indicators coupled to at least one of said upper surface and said lower surface, wherein said focus ring is configured to be centered about said substrate by coupling said focus ring to said centering ring,

wherein said centering ring is coupled to said substrate holder by at least one of said centering ring resting atop said substrate holder, said centering ring being mechanically clamped to said substrate holder, and said centering ring being electrically clamped to said substrate holder.

5. The focus ring assembly of claim 4, wherein said focus ring is made from at least one of silicon, quartz, silicon carbide, silicon nitride, amorphous carbon, alumina, sapphire, polyimide, and Teflon.

6. The focus ring assembly of claim 4, wherein said one or more wear indicators comprises a hole in said upper

8

surface and extending to a depth from said upper surface, said depth comprising a fraction of the distance between said upper surface and said lower surface.

7. The focus ring assembly of claim 4, wherein said one or more wear indicators comprise a hole in said lower surface and extending to a depth from said lower surface, said depth comprising a fraction of the distance between said upper surface and said lower surface.

8. The focus ring assembly of claim 6 or 7 wherein said depth for each of said one or more wear indicators varies from one wear indicator to another wear indicator.

9. The focus ring assembly of claim 4, wherein said centering ring comprises a centering feature configured to center said focus ring on said centering ring.

10. The focus ring assembly of claim 9, wherein said centering feature comprises at least one of a centering pin, a centering receptacle, and a centering edge.

11. The focus ring assembly of claim 9, wherein said focus ring comprises a mating feature configured to be coupled with said centering feature.

12. The focus ring assembly of claim 11, wherein said mating feature comprises at least one of a centering pin, a centering receptacle, and a centering edge.

13. The focus ring assembly of claim 4, wherein said centering ring is made from at least one of aluminum, coated aluminum, silicon, silicon carbide, silicon nitride, amorphous carbon, alumina, sapphire, polyimide, and Teflon.

14. The focus ring assembly of claim 13, wherein said centering ring is made from coated aluminum and comprises at least one of surface anodization, a plasma electrolytic oxidation coating, and a spray coating.

15. The focus ring assembly as recited in claim 13, wherein said centering ring is made from coated aluminum and comprises a coating having at least one of III-column element and a Lanthanum element.

16. The focus ring assembly as recited in claim 13, wherein said centering ring is made from coated aluminum and comprises a coating having at least one of Al_2O_3 , Yttria (Y_2O_3), Sc_2O_3 , Sc_2F_3 , YF_3 , La_2O_3 , CeO_2 , Eu_2O_3 , and DyO_3 .

* * * * *